Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-01-01-05** **Date: 12/03/2017**

Customer : Assistsnt Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing cement concrete roads to Inspector Ramaiah road and Surabhi Layout at Ward No.01

Agency : Sri.K.Achuta Murthy, No.07, 1st 'C' Main Road, Geleyan balaga, Mahalakhmipura, Bangalore-560086.

Customer's Reference : EE(Project)/YnkZone/Wo/79/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 01-01-18

Sample ID No : 2018-01-01-05/02

Customer ID : M20 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 12/03/2017

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Concrete	M20	12/02/2017	12/03/2017	150.33 X 150.30 X 150.27	22595	8.402	508.4	22.5	23.2
2	M20 Concrete	M20	12/02/2017	12/03/2017	150.31 X 150.29 X 150.30	22590	8.413	524.1	23.2	
3	M20 Concrete	M20	12/02/2017	12/03/2017	150.35 X 150.20 X 150.27	22583	8.378	537.5	23.8	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-01-09-02** **Date: 11/01/2018**

Customer : Assistsnt Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing cement concrete roads to Inspector Ramaiah road and Surabhi Layout at Ward No.01

Agency : Sri.K.Achuta Murthy, No.07, 1st 'C' Main Road, Geleyan balaga, Mahalakhmipura, Bangalore-560086.

Customer's Reference : EE(Project)/YnkZone/Wo/79/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 09-01-18

Sample ID No : 2018-01-09-02/01

Customer ID : Cement Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 11/01/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete	M20	04/01/2018	11/01/2018	150.32 X 150.38 X 150.37	22605	8.433	404.6	17.9	18.0
2	Cement Concrete	M20	04/01/2018	11/01/2018	150.28 X 150.25 X 150.31	22580	8.376	415.5	18.4	
3	Cement Concrete	M20	04/01/2018	11/01/2018	150.33 X 150.38 X 150.39	22607	8.445	397.9	17.6	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 01/02/2018

Lab ID	:	**CP-2018-01-09-02**
Customer	:	Assistsnt Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Providing cement concrete roads to Inspector Ramaiah road and Surabhi Layout at Ward No.01
Agency	:	Sri.K.Achuta Murthy, No.07, 1st 'C' Main Road, Geleyan balaga, Mahalakhmipura, Bangalore-560086.
Customer's Reference	:	EE(Project)/YnkZone/Wo/79/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	09-01-18
Sample ID No	:	2018-01-09-02/02
Customer ID	:	Cement Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	01/02/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete	M20	04/01/2018	01/02/2018	150.21 X 150.24 X 150.27	22568	8.332	530.3	23.5	22.5
2	Cement Concrete	M20	04/01/2018	01/02/2018	150.28 X 150.29 X 150.22	22586	8.355	505.9	22.4	
3	Cement Concrete	M20	04/01/2018	01/02/2018	150.28 X 150.20 X 150.25	22572	8.343	489.8	21.7	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-01-09-02** **Date: 11/01/2018**

Customer : Assistsnt Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing cement concrete roads to Inspector Ramaiah road and Surabhi Layout at Ward No.01

Agency : Sri.K.Achuta Murthy, No.07, 1st 'C' Main Road, Geleyan balaga, Mahalakhmipura, Bangalore-560086.

Customer's Reference : EE(Project)/YnkZone/Wo/79/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 09-01-18

Sample ID No : 2018-01-09-02/03

Customer ID : Cement Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 11/01/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete	M20	04/01/2018	11/01/2018	150.31 X 150.39 X 150.35	22605	8.433	393.3	17.4	17.5
2	Cement Concrete	M20	04/01/2018	11/01/2018	150.20 X 150.25 X 150.24	22568	8.345	404.0	17.9	
3	Cement Concrete	M20	04/01/2018	11/01/2018	150.21 X 150.32 X 150.22	22580	8.366	386.1	17.1	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-01-09-02** **Date: 01/02/2018**

Customer : Assistsnt Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing cement concrete roads to Inspector Ramaiah road and Surabhi Layout at Ward No.01

Agency : Sri.K.Achuta Murthy, No.07, 1st 'C' Main Road, Geleyan balaga, Mahalakhmipura, Bangalore-560086.

Customer's Reference : EE(Project)/YnkZone/Wo/79/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 09-01-18

Sample ID No : 2018-01-09-02/04

Customer ID : Cement Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 01/02/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete	M20	04/01/2018	01/02/2018	150.21 X 150.24 X 150.27	22568	8.324	521.3	23.1	23.4
2	Cement Concrete	M20	04/01/2018	01/02/2018	150.26 X 150.29 X 150.24	22583	8.354	535.2	23.7	
3	Cement Concrete	M20	04/01/2018	01/02/2018	150.28 X 150.20 X 150.25	22572	8.378	525.9	23.3	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-01-09-02** **Date: 11/01/2018**

Customer : Assistsnt Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing cement concrete roads to Inspector Ramaiah road and Surabhi Layout at Ward No.01

Agency : Sri.K.Achuta Murthy, No.07, 1st 'C' Main Road, Geleyan balaga, Mahalakhmipura, Bangalore-560086.

Customer's Reference : EE(Project)/YnkZone/Wo/79/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 09-01-18

Sample ID No : 2018-01-09-02/05

Customer ID : Cement Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 11/01/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete	M20	04/01/2018	11/01/2018	150.26 X 150.28 X 150.30	22581	8.356	408.7	18.1	17.7
2	Cement Concrete	M20	04/01/2018	11/01/2018	150.32 X 150.31 X 150.29	22595	8.412	388.6	17.2	
3	Cement Concrete	M20	04/01/2018	11/01/2018	150.26 X 150.30 X 150.24	22584	8.363	404.3	17.9	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-01-09-02** **Date: 01/02/2018**
Customer	:	Assistsnt Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Providing cement concrete roads to Inspector Ramaiah road and Surabhi Layout at Ward No.01
Agency	:	Sri.K.Achuta Murthy, No.07, 1st 'C' Main Road, Geleyan balaga, Mahalakhmipura, Bangalore-560086.
Customer's Reference	:	EE(Project)/YnkZone/Wo/79/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	09-01-18
Sample ID No	:	2018-01-09-02/06
Customer ID	:	Cement Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 01/02/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete	M20	04/01/2018	01/02/2018	150.22 X 150.24 X 150.27	22569	8.345	492.0	21.8	22.4
2	Cement Concrete	M20	04/01/2018	01/02/2018	150.28 X 150.29 X 150.30	22586	8.367	517.2	22.9	
3	Cement Concrete	M20	04/01/2018	01/02/2018	150.31 X 150.20 X 150.25	22577	8.323	505.7	22.4	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-01-09-02**

Date: 12/01/2018

Customer : Assistsnt Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing cement concrete roads to Inspector Ramaiah road and Surabhi Layout at Ward No.01

Agency : Sri.K.Achuta Murthy, No.07, 1st 'C' Main Road, Geleyan balaga, Mahalakhmipura, Bangalore-560086.

Customer's Reference : EE(Project)/YnkZone/Wo/79/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 09-01-18

Sample ID No : 2018-01-09-02/07

Customer ID : Cement Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 12/01/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete	M20	05/01/2018	12/01/2018	150.20 X 150.24 X 150.20	22566	8.336	413.0	18.3	18.2
2	Cement Concrete	M20	05/01/2018	12/01/2018	150.32 X 150.21 X 150.33	22580	8.378	415.5	18.4	
3	Cement Concrete	M20	05/01/2018	12/01/2018	150.38 X 150.32 X 150.38	22605	8.422	406.9	18.0	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 02/02/2018

Lab ID	:	**CP-2018-01-09-02**
Customer	:	Assistsnt Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Providing cement concrete roads to Inspector Ramaiah road and Surabhi Layout at Ward No.01
Agency	:	Sri.K.Achuta Murthy, No.07, 1st 'C' Main Road, Geleyan balaga, Mahalakhmipura, Bangalore-560086.
Customer's Reference	:	EE(Project)/YnkZone/Wo/79/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	09-01-18
Sample ID No	:	2018-01-09-02/08
Customer ID	:	Cement Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	02/02/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete	M20	05/01/2018	02/02/2018	150.28 X 150.32 X 150.29	22590	8.365	537.6	23.8	23.4
2	Cement Concrete	M20	05/01/2018	02/02/2018	150.25 X 150.28 X 150.20	22580	8.376	505.8	22.4	
3	Cement Concrete	M20	05/01/2018	02/02/2018	150.30 X 150.35 X 150.31	22598	8.425	540.1	23.9	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-01-09-02** **Date: 12/01/2018**

Customer : Assistsnt Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing cement concrete roads to Inspector Ramaiah road and Surabhi Layout at Ward No.01

Agency : Sri.K.Achuta Murthy, No.07, 1st 'C' Main Road, Geleyan balaga, Mahalakhmipura, Bangalore-560086.

Customer's Reference : EE(Project)/YnkZone/Wo/79/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 09-01-18

Sample ID No : 2018-01-09-02/09

Customer ID : Cement Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 12/01/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete	M20	05/01/2018	12/01/2018	150.26 X 150.28 X 150.27	22581	8.366	395.2	17.5	17.6
2	Cement Concrete	M20	05/01/2018	12/01/2018	150.28 X 150.29 X 150.30	22586	8.380	397.5	17.6	
3	Cement Concrete	M20	05/01/2018	12/01/2018	150.30 X 150.20 X 150.27	22575	8.367	401.8	17.8	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-01-09-02** **Date: 02/02/2018**

Customer : Assistsnt Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing cement concrete roads to Inspector Ramaiah road and Surabhi Layout at Ward No.01

Agency : Sri.K.Achuta Murthy, No.07, 1st 'C' Main Road, Geleyan balaga, Mahalakhmipura, Bangalore-560086.

Customer's Reference : EE(Project)/YnkZone/Wo/79/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 09-01-18

Sample ID No : 2018-01-09-02/10

Customer ID : Cement Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 02/02/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete	M20	05/01/2018	02/02/2018	150.31 X 150.32 X 150.29	22595	8.421	537.8	23.8	23.2
2	Cement Concrete	M20	05/01/2018	02/02/2018	150.34 X 150.28 X 150.32	22593	8.435	512.9	22.7	
3	Cement Concrete	M20	05/01/2018	02/02/2018	150.34 X 150.35 X 150.30	22604	8.446	522.1	23.1	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****